

InfinityOP™ Competitor Product Reference Guide

MFG	PRODUCTS	% VISIBLE LIGHT TRANSMISSION (VLT)	% TOTAL SOLAR ENERGY REJECTION (TSER)	% VISIBLE LIGHT REFLECTANCE (VLR)	% UV REJECTION	THICKNESS (mils)
SunTek	INF 65	65	40	8	99	1.5
Formula One	—	—	—	—	—	—
Llumar	—	—	—	—	—	—
Solar Gard	—	—	—	—	—	—
Madico	—	—	—	—	—	—
Johnson	Executive 60	59	36	10	99	n/a
ASWF	—	—	—	—	—	—
SunTek	INF 50	53	40	10	99	1.5
Formula One	—	—	—	—	—	—
Llumar	—	—	—	—	—	—
Solar Gard	Quantun 52	50	41	11	>99	1.5
Madico	—	—	—	—	—	—
Johnson	Executive 50	50	43	12	99	n/a
ASWF	Metallic 50	51	50	9	99	1.5
SunTek	INF 35	33	55	11	99	1.5
Formula One	—	—	—	—	—	—
Llumar	Platinum Plus 35	37	52	18	99	1.5
Solar Gard	Quantum 37	37	48	10	>99	1.5
Madico	—	—	—	—	—	—
Johnson	Executive 35	37	50	16	99	n/a
ASWF	Metallic 35	35	58	10	99	1.5
SunTek	INF 20	21	60	11	99	1.5
Formula One	—	—	—	—	—	—
Llumar	Platinum Plus 18	17	65	18	99	1.5
Solar Gard	Quantum 19	19	57	14	>99	1.5
Madico	—	—	—	—	—	—
Johnson	Executive 21	22	60	17	99	n/a
ASWF	Metallic 20	21	60	10	99	1.5
SunTek	INF 10	11	67	15	99	1.5
Formula One	—	—	—	—	—	—
Llumar	—	—	—	—	—	—
Solar Gard	Quantum 14	13	61	17	>99	1.5
Madico	—	—	—	—	—	—
Johnson	Executive 15	18	63	18	99	n/a
ASWF	Metallic 10	11	67	14	99	1.5

FormulaOne® and Llumar® are registered brand names of Solutia Inc.
 Solar Gard® is a registered brand name of Bekaert Specialty Films, LLC
 Madico® is a registered brand name of Madico, Inc.
 Johnson Window Films® is a registered brand name of Johnson Laminating & Coating, Inc.
 ASWF® is a registered brand name of Erickson International

The attached chart is to be used for comparison purposes only.
 Competitive information and product specifications obtained from formulaone.com, llumar.com, solargard.com, madico.com, johnsonwindowfilms.com and aswf.com on 2/11/2011